



**NAPCON-1000 / DM**



**NAPCON-1450**



**NAPCON-7000**



**NAPCON BP-107**

Pad	1000 DM	1000	7000	1450	BP-107
Surface	Machined	Buffed	Buffed	Non-Buffed	Buffed
AVG Film Thickness (µm)	525 ±15	520 ±20	590 ±30	610 ±50	390 ±30
Pore Height (µm)	300~390	300~390	300~390	N/A	100~190
Pore Diameter (µm)	35~55	35~55	33~53	N/A	41~51
Pore Rate (%)	18~28	18~28	20~30	N/A	18~28
Compressibility (%)	27~37	27~37	6~20	3~7	13~23